

PRODUCT DATA

FSP-SC > Sprayable core material, thick and lightweight topcoat

Reference	Application	Viscosity / poises	Thix. Index	Density (± 0,05)	Gel time / min (on 130gr mass, at 20°C, 2% MEKP 50)	Comments
FSP-SC 1527	Spray	550-700	≥ 5	0,7	15-20	Application in sandwich construction, to replace fiberglass, felt, foam, and other core materials. High mechanical properties, high rigidity, no water uptake. Significant time savings, no roll, application up to 5mm in vertical without sagging. Improved surface quality (low exotherm, low shrink, fiber-marking reduction) Low styrene content.
FSP-TC 1560	Spray	500-650	3,5	0,7	15-25	Application as a thick top coat, to fill the surface defects of laminates. Good surface tension. Can be laminated over without sanding.

For further information please refer to Products & Applications pages: euromere.com



Download this pdf : File > Save as