

FSP® SC Spray Coring

Sprayable core material, thick and lightweight top coat

Reference	Application	Viscosity/peas	Thixo index	Density (± 0,05)	Gel/min time (on a 130 gr mass at 20 °C, 2% MEKP 50)	Comments
FSP-SC 1527	Spray app	550 – 700	≥ 5	0,7	15 – 20	Application in sandwich construction, replacing fiberglass, felt, foam and other core products. High mechanical properties, high rigidity, no water absorption. Significant time savings, no chipping, application up to 5mm vertically without sagging. Improved surface appearance (low exotherm, limited shrinkage, reduced marking). Low styrene content.